Properties	EPDM	Butyl	Poly- chloro- prene	PVC	PU	Modified bitumen	Bituminous build-up roofing
Dimensional stability	E	G	G	F	F	F	F
Resistance to:							00/410/1 (0.50/m)
High temperature	E	G	F	P	F	P	P
Ozone	E	G	G	G	G	F	F
UV	E	G	G	F	G	F	G
Cold cracking	E	G	F	F	F	P	P
Weather	E	G	G	F	F	P	P
Acids and alkalies	E	G	E	G	F	NA	NA
Cost effectiveness	Less expensive	Very expensive	Very expensive	Expensive	Very expensive	Expensive	Expensive

F: Fair

P: Poor

Source: Polymers In Construciton, Guneri Akovali, Pg 85